

## Epoxy Zinc-Rich

### PRODUCT DESCRIPTION

A two component, metallic zinc rich epoxy which complies with the compositional requirements of SSPC Paint 20 Level 1.

### INTENDED USES

As a high performance primer to give maximum protection as part of any anti-corrosive coating system for aggressive environments including those found on petrochemical facilities, bridges and power plants.

Interzinc 5285 has been designed to provide excellent corrosion resistance in both industrial maintenance and new construction situations.

### PRACTICAL INFORMATION FOR INTERZINC 5285

<b>Colour</b>	Grey
<b>Gloss Level</b>	Matt
<b>Volume Solids</b>	59%
<b>Typical Thickness</b>	50-75 microns (2-3 mils) dry equivalent to 85-127 microns (3.4-5.1 mils) wet
<b>Theoretical Coverage</b>	11.80 m <sup>2</sup> /litre at 50 microns d.f.t and stated volume solids 473 sq.ft/US gallon at 2 mils d.f.t and stated volume solids
<b>Practical Coverage</b>	Allow appropriate loss factors
<b>Method of Application</b>	Air spray, Airless spray, Brush

#### Drying Time

Temperature	Touch Dry	Hard Dry	Overcoating Interval with recommended topcoats	
			Minimum	Maximum
5°C (41°F)	2 hours	10 hours	8 hours	Extended <sup>1</sup>
15°C (59°F)	90 minutes	6 hours	4 hours	Extended <sup>1</sup>
25°C (77°F)	75 minutes	4 hours	3 hours	Extended <sup>1</sup>
40°C (104°F)	45 minutes	2 hours	2 hours	Extended <sup>1</sup>

<sup>1</sup> See International Protective Coatings Definitions and Abbreviations

### REGULATORY DATA

<b>Flash Point (Typical)</b>	Part A 29°C (84°F); Part B 30°C (86°F); Mixed 29°C (84°F)		
<b>Product Weight</b>	2.62 kg/l (21.9 lb/gal)		
<b>VOC</b>	153 g/kg	EU Solvent Emissions Directive (Council Directive 1999/13/EC)	
See Product Characteristics section for further details			

## Epoxy Zinc-Rich

### SURFACE PREPARATION

All surfaces must be clean, dry, and free of oil, grease, dust, and other contaminations. To ensure the best appearance, the primer or undercoat should be smooth and free of any surface defects, such as runs, dry spray or heavy orange peel. Prior to paint application, all surfaces should be assessed and treated in accordance with ISO 8504:2000.

Oil or grease should be removed in accordance with SSPC-SP1 solvent cleaning.

#### Abrasive Blast Cleaning

Abrasive blast clean to a minimum of Sa2½ (ISO 8501-1:2007) SSPC-SP6. If oxidation has occurred between blasting and application of Interzinc 5285 the surface should be re-blasted to the specified visual standard. Surface defects revealed by the blast cleaning process should be ground, filled, or treated in the appropriate manner.

A surface profile of 40-75 microns (1.6-3.0 mils) is recommended.

#### Shop Primed Steelwork

Interzinc 5285 is suitable for application to unweathered steelwork freshly coated with zinc silicate shop primers.

If the zinc shop primer shows extensive or widely scattered breakdown, or excessive zinc corrosion products, overall sweep blasting will be necessary. Other types of shop primer are not suitable for overcoating and will require complete removal by abrasive blast cleaning.

Weld seams and damaged areas should be cleaned to a minimum St3 (ISO 8501-1:2007) or SSPC-SP3. Optimum performance will be achieved with blasting to Sa2½ (ISO 8501-1:2007) or SSPC-SP6; where this is not practical, hand preparation to SSPC-SP11 is recommended.

### APPLICATION

<b>Mixing</b>	Material is supplied in two containers as a unit. Always mix a complete unit in the proportions supplied. Once the unit has been mixed it must be used within the working pot life specified.		
	(1) Agitate Base (Part A) with a power agitator. (2) Combine entire contents of Curing Agent (Part B) with Base (Part A) and mix thoroughly with power agitator.		
<b>Mix Ratio</b>	4 part(s) : 1 part(s) by volume		
<b>Working Pot Life</b>	5°C (41°F) 24 hours	15°C (59°F) 12 hours	25°C (77°F) 40°C (104°F) 5 hours 2 hours
<b>Airless Spray</b>	Recommended	Tip Range 0.43-0.53 mm (17-21 thou) Total output fluid pressure at spray tip not less than 176 kg/cm <sup>2</sup> (2503 p.s.i.)	
<b>Air Spray (Pressure Pot)</b>	Recommended	Gun Air Cap Fluid Tip	DeVilbiss MBC or JGA 704 or 765 E
<b>Air Spray (Conventional)</b>	Recommended	Use suitable proprietary equipment	
<b>Brush</b>	Suitable	Typically 50-75 microns (2.0-3.0 mils) can be achieved	
<b>Roller</b>	Not recommended		
<b>Thinner</b>	International GTA220 (or International GTA415)	Do not thin more than allowed by local environmental legislation	
<b>Cleaner</b>	International GTA822 (or International GTA415)		
<b>Work Stoppages</b>	Do not allow material to remain in hoses, gun or spray equipment. Thoroughly flush all equipment with International GTA822. Once units of paint have been mixed they should not be resealed and it is advised that after prolonged stoppages work recommences with freshly mixed units.		
<b>Clean Up</b>	Clean all equipment immediately after use with International GTA822. It is good working practice to periodically clean equipment during the course of the working day. Frequency of cleaning will depend upon amount used, temperature and elapsed time, including any delays.		
	All surplus materials and empty containers should be disposed of in accordance with appropriate regional regulations/legislation.		

## Epoxy Zinc-Rich

### PRODUCT CHARACTERISTICS

In order to ensure good anti-corrosive performance, it is important to achieve a minimum dry film thickness of Interzinc 5285 of 40 microns (1.5 mils). To achieve a uniform, coalesced, closed film at this dry film thickness, it will be necessary to thin Interzinc 5285 10% with International thinners. The film thickness of Interzinc 5285 applied must be compatible with the blast profile achieved during surface preparation. Low film thickness should not be applied over coarse blast profiles.

Care should be exercised to avoid the application of dry film thicknesses in excess of 150 microns (6 mils).

Care should be exercised to avoid over-application, which may result in cohesive film failure with subsequent high builds, and to avoid dry spray which can lead to pinholing of subsequent coats. Over-application will also result in slower curing and extended handling and overcoating times.

Over-application of Interzinc 5285 will extend both the minimum overcoating periods and handling times, and may be detrimental to long term overcoating properties.

When Interzinc 5285 is allowed to weather before topcoating ensure all zinc salts are removed prior to paint application and only topcoat with recommended materials.

Surface temperature must always be a minimum of 3°C (5°F) above dew point.

Interzinc 5285 is suitable for the localised repair of damaged inorganic zinc primer - consult International Protective Coatings for specific advice.

### Low Temperature Curing

An alternative curing agent is available for applications at temperatures less than 5°C (41°F). When using this alternative curing agent it should be noted that the VOC will increase to 360 g/l (3 lb/gal).

Interzinc 5285 is capable of curing at temperatures below 0°C (32°F). However, this product should not be applied at temperatures below 0°C (32°F) where there is a possibility of ice formation on the substrate.

Temperature	Touch Dry	Hard Dry	Minimum overcoating interval with recommended topcoats	
			<i>Minimum</i>	<i>Maximum</i>
-5°C (23°F)	6 hours	32 hours	36 hours	Extended*
0°C (32°F)	3 hours	16 hours	18 hours	Extended*
5°C (41°F)	2 hours	6 hours	6 hours	Extended*

Touch dry times shown above are actual drying times due to chemical cure, rather than physical set due to solidification of the coating film at temperatures below 0°C (32°F)

\* See International Protective Coatings Definitions & Abbreviations

For further details regarding cure times and overcoatability, please contact International Protective Coatings.

Note: VOC values are typical and are provided for guidance purpose only. These may be subject to variation depending on factors such as differences in colour and normal manufacturing tolerances.

Low molecular weight reactive additives, which will form part of the film during normal ambient cure conditions, will also affect VOC values determined using EPA Method 24.

### SYSTEMS COMPATIBILITY

Interzinc 5285 is designed for application to correctly prepared steel. However, it is also possible to apply over approved prefabrication primers. Further details of these can be obtained from International Protective Coatings.

Recommended topcoats are:

Intercure 200	InterH2O 401
Intercure 420	Interseal 670HS
Interfine 629HS	Interthane 990
Intergard 251	Interzone 1000
Intergard 269	Interzone 505
Intergard 475HS	Interzone 954
Intergard 740	

For other suitable topcoats, consult International Protective Coatings.

## Epoxy Zinc-Rich

### ADDITIONAL INFORMATION

Further information regarding industry standards, terms and abbreviations used in this data sheet can be found in the following documents available at [www.international-pc.com](http://www.international-pc.com):

- Definitions & Abbreviations
- Surface Preparation
- Paint Application
- Theoretical & Practical Coverage

Individual copies of these information sections are available upon request.

### SAFETY PRECAUTIONS

This product is intended for use only by professional applicators in industrial situations in accordance with the advice given on this sheet, the Material Safety Data Sheet and the container(s), and should not be used without reference to the Material Safety Data Sheet (MSDS) which International Protective Coatings has provided to its customers.

All work involving the application and use of this product should be performed in compliance with all relevant national, Health, Safety & Environmental standards and regulations.

In the event welding or flame cutting is performed on metal coated with this product, dust and fumes will be emitted which will require the use of appropriate personal protective equipment and adequate local exhaust ventilation.

If in doubt regarding the suitability of use of this product, consult International Protective Coatings for further advice.

PACK SIZE	Unit Size	Part A		Part B	
		Vol	Pack	Vol	Pack
	10 litre	8 litre	10 litre	2 litre	2.5 litre
For availability of other pack sizes, contact International Protective Coatings.					
SHIPPING WEIGHT (TYPICAL)	Unit Size	Part A		Part B	
		25.84 kg		2.27 kg	
	10 litre				
STORAGE	Shelf Life	12 months minimum at 25°C (77°F). Subject to re-inspection thereafter. Store in dry, shaded conditions away from sources of heat and ignition.			

### Important Note

*The information in this data sheet is not intended to be exhaustive; any person using the product for any purpose other than that specifically recommended in this data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at their own risk. All advice given or statements made about the product (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing to do so, we do not accept any liability at all for the performance of the product or for (subject to the maximum extent permitted by law) any loss or damage arising out of the use of the product. We hereby disclaim any warranties or representations, express or implied, by operation of law or otherwise, including, without limitation, any implied warranty of merchantability or fitness for a particular purpose. All products supplied and technical advice given are subject to our Conditions of Sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is liable to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to check with their local representative that this data sheet is current prior to using the product.*

*This Technical Data Sheet is available on our website at [www.international-marine.com](http://www.international-marine.com) or [www.international-pc.com](http://www.international-pc.com), and should be the same as this document. Should there be any discrepancies between this document and the version of the Technical Data Sheet that appears on the website, then the version on the website will take precedence.*

Copyright © AkzoNobel, 05/02/2015.

All trademarks mentioned in this publication are owned by, or licensed to, the AkzoNobel group of companies.

[www.international-pc.com](http://www.international-pc.com)